

Nombre/Name	Rolls Royce MSRR	AMS	British Standard	UNS	ASTM	Werkstoff No.
NIMONIC 75	7004/7104		HR 5/203/504	N 06075	B637	2.4630
NIMONIC 80A	7011/7013		HR1/HR601/HR201 3076 NA 20	N 07080		2.4952 2.4631
NIMONIC 86	7141/7152					
NIMONIC 90	7137/7016	5829	HR2/202 3075 NA 20	N 07090		2.4632
NIMONIC105	7063/7162		HR 3			2.4634
NIMONIC 115	7022/7193		HR 4			2.4636
NIMONIC C263	7035/7036	5872/5886	HR 10/206	N 07263		2.4650
NIMONIC PE 11	7181/7182					
NIMONIC PE 16	7070/7952		HR 55, 2007			
NIMONIC PK 33	7166/7195					
INCONEL 617		5887/8/9				
INCONEL 625 LCF/DDQ		5599/5666 5879	3076 NA 21	N 06625	B443/B 446	2.4856
INCONEL 718	7115/7116	5662/5663/5596		N 07718	B637/B 670	2.4668
INCONEL X750		5670/5671 5667/5598	HR 505	N 07750	B637	2.4699
ALLOY X	7127	5536/5754/5798	HR 6, 204		B435	2.4665
ALLOY L605/26	7052/7053	5759/5796				
JETHETE M152	6503/6666 6502/6916	5718/9	S151		A565	
A286	6531/6532	5731/5732 5734/5737	HR 51/52/650		A453/63 8 660A & B	1.4943 1.4944
MARAGING 250			S162			
TITANIUM 6AL4V	8614/8652	4928/4967	TA11/12/7252 pt3		B348 Gr 5	3.7164
TITANIUM GRADE 2					B348	2.4819
ALLOY C276				N 10276	B574	
DUREHETE 900			1506-631-850			
DUREHETE 950			1506-671-850			
DUREHETE 1055			1506-681-820			
X19						1.4913
21 Cr.MoV5.7						1.7707
WASPALOY						
A181 422						
13/8 PH		5629				
15/5 PH		5659				
17/4 PH		5622/5643				

Para más Información puede mandarnos un correo electrónico a la siguiente dirección:

- [info@reingosum.com](mailto:info@reingosum.com)

También puede llamarnos a: - 944 277 093

- 669 785 604